

**IN THE SPECIFICATION:**

Please amend Page 5, Lines 9-12 to read as follows:

Please note that it is confirmed that cracks are more effectively restrained by adjusting the crystal [[rain]] grain diameter  $G$  ( $\mu\text{m}$ ) of polycrystalline alumina ceramic to be in a range of 0.5 to 1.5, inclusive.